

Chongqing Polycomp International Corp.

Jianqiao Industiral Park B, Dadukou District Chongqing, China.

Post code: 400082 website: www.cpicfiber.com

Technical support . Tel: (+86-23)68157743 (+86-23)68157178

Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586

Fax: (+86-23)68157822

Chopped Strand for BMC ECS403

Identification

Example: ECS403-6-L

ECS: E-glass Chopped strands

Sizing code: 403

Chopped length (mm): 6 Filament diameter: 13.7



Product Description

Specially designed for BMC processing . Applied in ceiling, electric switch, lampshade etc..

Product Benefits

- Good flowability
- Good wetting.
- Easy coloring
- Good appearance for fiber and finished goods
- Perfect impact strength

Technical Characteristics

Compatible Resin	Diameter (µm)	Moisture Content (%)	Loss on Ignition (%)	Bulk Density (g/ cm3)
/	ISO 1888	ISO 3344	ISO 1887	ISO 15100
UP、VE	±1	≤0.01	0.8±0.1	0.7±0.15

Product code	Glass Type	Filament diameter[µm]	Chopped length [mm]
ECS403	ECT	13.7	6、12



Chongqing Polycomp International Corp.
Jianqiao Industiral Park B, Dadukou District Chongqing, China. Post code: 400082 website: www.cpicfiber.com Technical support . Tel: (+86-23)68157743 (+86-23)68157178 Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586 Fax: (+86-23)68157822

Packing

Package Method	Package weight [kg]	Quantity	Pallet size [mm] Length*width*height
Super sack bag	1000	1 pallet	1140*1140*1100
Poly-plastic film bag	25	40 bags	850*500*120

Pallets illustration



Note: Products can be packed according to the customer's request.

Storage

- If no special requirements, it should be stored in cool and dry place . The recommended temperature range is 10-30 °C, humidity should be 50 -75%.
- The product should be always kept package encapsulation before use.
- Pallet stacking height should not over 1 layer.







